


Bolphane® BY

Multipurpose polyolefin shrink film with high yield

- Outstanding yield.
- Optimum shrinkage in low energy use.
- Excellent sealing performance .
- Hot slip properties after shrinkage.

APPLICATIONS

- ➔ Unique technical capabilities enable Bolphane BY to give excellent result from manual to automatic high speed machines.




- ➔ High shrinkage performance, good optics, outstanding machinability : Bolphane BY is very versatile and performing on a large variety of systems.

Bolloré

Bolphane[®] BY

SHRINK PROFILE

- Compared to a standard polyolefin film, Bolphane BY demonstrates higher shrink capability up to 20%.



TECHNICAL FEATURES

→ PROPERTIES	13 MICRONS	15 MICRONS	19 MICRONS	25 MICRONS
Gloss (85° angle) in %	118			
Haze (%)	2,5			3
Shrinkage (%)	at 93°C			
	30			
Seal strength (N/30 mm)	at 120°C			
	25	27	37	45
Water steam permeability (g/m ² /24hr at 35°C-95% RH)	at 150°C			
	50	60	70	85
O ² Permeability (cm ³ /m ² /24hr bar)	24	20	16	12
Length of the roll (m)	Singlewound BY-S			
	3 100	2 670	2 140	1 600
Internal diameter (mm)	Centrefolded BY-C			
	1 550	1 335	1 070	800
External diameter (mm)	76,2			
	245			

PRESENTATION

- Bolphane BY exists in Singlewound (BY-S) or in Centerfolded (BY-C). For any specific request, please refer to the commercial documentation.

→ VERSION	WIDTH (mm)		
	mini	maxi	increment
BY-S	150	1 400	5
BY-C	150	1 000	10

The technical features of the products defined herein are given as typical values. They are guides for the use of the quoted films values and are not for use as limiting specification. Users have to check-up that they are suitable with all the applications as performance may vary with processing conditions. Properties and performance are subject to change and BOLLORÉ keeps the right to modify the definition and properties of its products without prior notice.

Bolloré